




Clay & Pottery Supplies 2985 Haldimand Rd. 9 York, ON, NOA 1RO (905) 379-5868 info@clayandpotterysupplies.com



Technical Data

Firing Range:	Cone 5-10
Biscuit Temperature:	Cone 06
Water Content:	19%
Plasticity (IP Atterberg):	16
Carbonate Content (CaCO3):	0%
Drying Shrinkage:	5.7%
Firing Shrinkage (1250°C):	6.4%
Porosity (1250°C):	0.1%
Dry Bending Strength:	2.9 N/mm ²
Fired Bending Strength (1250°C):	53.2 N/mm ²
Thermal Coefficient (1250°C):	60.1x10 ^{-7°} C ⁻¹

Features





High-Fire Stoneware Clay



Suitable For Tableware (Food-safe according to ISO 6486:1999 standards) Microwave-Safe



Technical Data Sheet Berlin Grey Stoneware High-Fire Clay

SIO-2[®] Berlin is crafted with 40% impalpable grog, offering a distinctive texture and finish for your creations. The grog helps minimize shrinkage and cracking, making it an excellent choice for large sculptures. Formulated for artistic ceramics, it's ideal for both modeling and wheel-throwing.

A standout feature of SIO-2[®] Berlin is its ability to capture fine details, enabling artists to create intricate, avant-garde, and delicate sculptures.

This amazing ceramic clay showcases a large range of greys, from modern cement tones to rich dark greys, depending on the firing range.

Available Packaging

Full-Size 27.6 lbs

Sample-Size 4 lbs

