



Clay & Pottery Supplies
2985 Haldimand Rd. 9
York, ON, N0A 1R0
(905) 379-5868
info@clayandpotterysupplies.com



Technical Data Sheet

PF

Red Earthenware

Low-Fire Clay

Technical Data

Firing Range:	Cone 06-04
Biscuit Temperature:	–
Water Content:	22%
Plasticity (IP Atterberg):	17
Carbonate Content (CaCO3):	10%
Drying Shrinkage:	5.5%
Firing Shrinkage (1250°C):	0.6%
Porosity (1250°C):	13.5%
Dry Bending Strength:	6.6 N/mm ²
Fired Bending Strength (1250°C):	27.9 N/mm ²
Thermal Coefficient (1250°C):	77.7x10 ⁻⁷ °C ⁻¹

Features



Low-Fire Earthenware Clay



**Not Tested For Use
In Microwave**



**Not Suitable
For Tableware**



**Compatible With Most
Standard Glazes**
(Test firing recommended)

Available Packaging

Full-Size
27.6 lbs

Sample-Size
4 lbs



WWW.CLAYANDPOTTERYSUPPLIES.COM • 2024